

# Strength of Concrete C Different Types of Fine Aggregates

Sarjak Chawda<sup>1</sup>, Aditi Patil<sup>2</sup>, Abhishek Singh<sup>3</sup>, Ashwini Save<sup>4</sup>

Department of Civil Engineering, Mumbai University, INDIA

**Abstract**— Common river sand is expensive due to excessive cost of transportation from natural sources. Also large-scale depletion of these sources creates environmental problems. As environmental transportation and other constraints make the availability and use of river sand less attractive, a substitute or replacement product for concrete industry needs to be found. River sand is most commonly used fine aggregate in the production of concrete poses the problem of acute shortage in many areas. Whose continued use has started posing serious problems with respect to its availability, cost and environmental impact? An attempt has also been made for strength studies on concrete made up of grit when compared with the concrete made up of Artificial Sand and Natural Sand. Use of grit as a fine aggregate in concrete draws serious attention of researchers and investigators.

**Keywords**— Artificial Sand, depletion of sources, environmental transportation, fine aggregate, Grit, Natural Sand, replacement product.

## I. INTRODUCTION

Currently India has taken a major initiative on developing the infrastructures such as express highways, power projects and industrial structures etc. To meet the requirements of globalization, in the construction of buildings and other structures concrete plays the rightful role and a large quantum of concrete is being utilized. River sand, which is one of the constituents used in the production of conventional concrete, has become highly expensive and also scarce. In the backdrop of such a bleak atmosphere, there is large demand for alternative materials from industrial waste. The utilization of Grit which can be called as dust of quarry rock has been accepted as a building material. As a result of sustained research and developmental works undertaken with respect to increasing application of this industrial waste. The level of utilization of Grit in the industrialized nations like Australia, France, Germany and UK has been reached more than 60% of its total production. The use of manufactured sand in India has not been much, when compared to some advanced countries. This paper presents the feasibility of the usage of Grit as hundred percent substitutes for Conventional Concrete. Tests were conducted on cubes and beams to study the strengths of concrete made of Grit as a waste material, artificial sand and natural sand. Studies were done for concrete with Grit, artificial sand and compared with the Conventional Concrete.

II.

## III. METHODOLOGY

Assessment is made on the existing mix design methods and test results of concrete produced using manufactured sand. Tests were conducted using river sand, manufactured sand and a combination of both with equal amounts of cement, coarse aggregate and water and with variable amounts of admixtures. A cost comparison of concrete produced using partial or full replacement of the Natural Sand with Manufactured Sand was made. The results were presented in graphical form and interpretation and discussion were made on the research findings. Based on the findings conclusions are drawn and recommendations are forwarded.

## IV. PRACTICAL PROBLEMS

Concrete does not give adequate workability because particle shape is not spherical but cubical or flaky. This can be controlled by proper shape and gradation, use of plasticizers etc. Higher water absorption removes free water also greater surface area results in faster evaporation by which concrete tends to set quickly. Use of retarding plasticizers, protecting the green concrete from drying can cover these problems. Concrete tends to segregate due to flaky shape, lack of adequate fines, segregation of particles while transportation and Unloading. Segregation during transportation can be prevented by spraying water, blending

with natural sand, use of fibers to increase cohesion. Sometimes Concrete gives lower strength because of flaky particles or higher fines increase water demand, higher water demand translates in to higher water cement ratio. Controlling the quality of incoming material by visual inspection and regular sieve analysis solve such problems. Lower workability, lower slump retention, and inadequate vibration, segregation of concrete also managed by use of plasticizers, retarders and fly ash, complete compaction and finishing as early as possible.

## V. DISCUSSIONS

From above test results, we came to know that Grit has proven to be highest compressible strength fine aggregate as compared to Natural Sand, Artificial Sand & combination of Natural Sand & Artificial Sand. In case of Beam the ultimate load for Artificial Sand is found to be maximum of 32KN with deflection 2.96mm and that of Grit with minimum ultimate load of 30KN with deflection 2.60mm .Grit gives maximum compressive strength 41.43MPa as compared to Natural Sand, Artificial Sand & combination of Natural Sand & Artificial Sand, which found to be 5% more with 100% replacement of Natural Sand in conventional concrete mix .In case of cylinder for Tensile strength, Grit has given maximum Tensile strength 7.12 MPa, which is quite more than other.

## VI. CONCLUSION

From the above results and discussion we conclude that among the above four fine aggregate samples like Natural Sand, Artificial sand, Grit & Combination of both N.S.& Ar.Sand; Grit gives the maximum compressive strength. Though grit and artificial sand gives nearly same results, grit is more preferable than artificial sand as it's more eco-nominal .Grits of various types obtained from various sources affects the strength and durability of concrete while compare a-timely more uniqueness is achieved in case of artificial sand .The use of manufactured sand in the construction Indus-try helps to prevent unnecessary damages to the environment and provide optimum exploitation of the resources. Manufactured sands are made by crushing aggregate to sizes appropriate for use as a fine aggregate. During the crushing process the manufactured sand have irregular shapes and more fine particles contributing to improved compressive strength, compared to natural sand control mix. Due to the irregular particle shape of the manufactured sand, in addition to the reduced amount of water cement ratio, manufactured sand is more important for high strength concrete mixes.

## REFERENCES

- [1] M. Shahul Hameed and A. S. S. Sekar, JUNE 2009," *Properties OfGreen Concrete Containing Quarry Rock Dust And Marble Sludge Powder As Fine Aggregate*", ARPJ Journal of Engineering and Applied Sciences, VOL. 4, NO. 4- ISSN 1819-6608
- [2] R. Ilangothana, N. Mahendrana and K. Nagamanib, OCTOBER2008, " *Strength And Durability Properties Of Concrete ContainingQuarry Rock Dust As Fine Aggregate* ", ARPJ Journal of Engineer-ing and Applied Sciences, VOL. 3, NO. 5- ISSN 1819-6608
- [3] Mahendra R. Chitlange and Prakash S. Pajgade, OCTOBER 2010,"*Strength Appraisal Of Artificial Sand As Fine Aggregate In Sfr*", ARPJ Journal of Engineering and Applied Sciences-VOL. 5, NO. 10- ISSN 1819-6608
- [4] V.R.K. Narasinha Rajul and T. Appa Reddy, (2009)," *Workabilityand Strength characteristics of Cement Concrete with Partial Replacement of River Sand by Manufactured Fine aggregate*", International Journal of Mechanics and Solids, ISSN 0973-1881 Volume 4, Number 1, pp. 95-104
- [5] L. Zeghichi, (2006)," *The Effect Of Replacement Of Natural Aggre-gates By Slag Products On The Strength Of Concrete*", Asian Journalof Civil Engineering (Building And Housing) Vol. 7, Pages 27-35
- [6] Radhikesh P. Nanda , Amiya K. Das , Moharana.N.C, 2010,"*Stone crusher dust as a fine aggregate in Concrete for paving blocks*", Volume 1, No 3, ISSN 0976 – 4399.